



Face Material

weight

60±10%g/m² ISO 536

thickness

0.07±10%mm ISO 534

material

uncoated white matt paper

Liner

55 ±10%g/m² ISO 536

0.055±10%mm ISO 534

Single-color plastic-coated white CCK release paper

Adhesive

This is an adhesive with a high initial viscosity. High-tack, permanent acrylic adhesive ideal for non-polar surfaces.

Peel adhesion

Initial adhesion
8N/25mm FTM 9 st.st

20 minutes Peel adhesion value on steel at 180° 9N/25mm or tear off FTM 1 st.st

20 minutes Peel adhesion value on steel at 90° 5N/25mm or tear off FTM 2 st.st

Temperature

Min. Appl. Temp. 10 °C

Service Temp. -35~90°C (after 24hrs)

Applications

This product has good adhesion properties and is widely used in price tags, computer printed labels and matte labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Siga. All sales of Siga products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

The surface material has excellent ink absorption and is suitable for a variety of printing methods, including laser and inkjet printing. Matte paper with a rough surface, suitable for printing and printing of simple graphics. Used in office, logistics and other industries.

Shelf life

12 months, applicable only to the material delivered by Siga which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23±2°C and 50±5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.