



**Face Material**

weight	thickness	material
100g / m <sup>2</sup> ± 10% ISO536	120μ ± 10% ISO534	Glossy White fine sand pattern paper

**Liner**

60g / m <sup>2</sup> ± 10% ISO536	53μ ± 10% ISO534	Super calendered semi-gloss white glassine liner
-----------------------------------	------------------	--

**Adhesive**

General-purpose hot melt adhesive with high initial tack and excellent performance on many packaging materials. Not suitable for application on PVC surfaces. Bottles with small diameters and irregular surfaces or frequently squeezed are not recommended. A comprehensive labeling test must be conducted in the final use environment before applied. Suitable for low temperatures or rough surfaces. Usually used with films.

**Peel adhesion**

initial adhesion 14 N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180° 16N/25mm or tear off FTM 1 st.st	20 minutes Peel adhesion value on steel at 90° 8N/25mm or tear off FTM 2 st.st
---	--	--

**Temperature**

Min. Appl. Temp. 10°C	Service Temp.-15~65°C (24H after labeling)
-----------------------	--

**Applications**

Typically it is used to make label on red wine, food, etc.

The above suggestion, application, and elaboration are not intended as the guarantee of Siga. All sales of Siga products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

**Printing Methods**

Avoid material deformation caused by overheating. It can be applied to various printing methods such as flexographic printing, letterpress printing and screen printing, and has good expressiveness to ink.

**Shelf life**

12 months, applicable only to the material delivered by Siga which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.