



Face Material

weight	thickness	material
46±10%/m ² ISO 536	0.050±10%mm ISO 534	Biaxially oriented transparent polypropylene film with special coating

Liner

58±10%/m ² ISO 536	0.055±10%mm ISO 534	White glassine treated with super calender
-------------------------------	---------------------	--

Adhesive

General-purpose permanent rubber-based adhesive with high viscosity and excellent processing performance. It has a good performance on the surface of glass, stainless steel, PE, PP, cartons and other materials that do not contain plasticizers.

Peel adhesion

Initial adhesion 17N/25mm FTM 9 st.st	20minutes Peel adhesion value on steel at 180° 18N/25mm FTM 1 st.st	20minutes Peel adhesion value on steel at 90° 9N/25mm FTM 2 st.st
--	---	---

Temperature

Min. Appl. Temp. 5 °C	Service Temp. -35~65°C (24H after labeling)
-----------------------	---

Applications

The material has a certain degree of tear resistance and chemical corrosion resistance, and is widely used in labels in industries such as washing, cosmetics, daily chemicals, food and electronic labels. Has good transparency and a certain degree of fragility.

The above suggestion, application, and elaboration are not intended as the guarantee of Siga. All sales of Siga products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

There is a layer of coating on the surface that is transparent. Avoid material deformation caused by overheating. Applicable to various printing methods such as flexographic printing, letterpress printing and screen printing, etc., and has good expressive power for inks. Product labels with more important properties such as water resistance, oil resistance and chemical substances..

Shelf life

12 months, applicable only to the material delivered by Siga which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23±2°C and 50±5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.