



**Face Material**

weight	thickness	material
65±10%g/m <sup>2</sup> ISO 536	0.045±10%mm ISO 534	Holographic PP with square printing

**Liner**

58±10%g/m <sup>2</sup> ISO 536	0.055±10%mm ISO 534	Yellow glassine treated with super calender
--------------------------------	---------------------	---

**Adhesive**

Permanent high-viscosity water-based acrylic pressure-sensitive adhesive for film has high viscosity, is suitable for a variety of substrates, and has excellent adhesion effects on a variety of material surfaces

**Peel adhesion**

Initial adhesion 8N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180° 9N/25mm FTM 1 st.st	20 minutes Peel adhesion value on steel at 90° 5N/25mm FTM 2 st.st
---	--	---

**Temperature**

Min. Appl. Temp. 10 °C	Service Temp. -35~90°C (after 24hrs)
------------------------	--------------------------------------

**Applications**

The product has certain tear resistance, dimensional stability and chemical corrosion resistance, and is suitable for making various labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Siga. All sales of Siga products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

**Printing Methods**

The surface has been treated with a special coating, which can meet various printing methods. It is recommended to die-cut with a high-hardness tool, and at the same time avoid label overflow due to excessive winding tension. Provides excellent stiffness and clarity, good printability and die-cutting properties, excellent chemical and UV resistance.

**Shelf life**

12 months, applicable only to the material delivered by Siga which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23±2°C and 50±5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.